NOTES:

- SUBSTRATE
- 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN 5 arcsec
- 3. COATING (APPLY ACROSS COATING APERTURE) ENVIRONMENTAL DURABILITY:

PHYSICAL DURABILITY:

PERFORMANCE SPECIFICATIONS:


T(avg):>85% FROM 325 - 430 nm FOR RANDOM POLARIZATION @ 45° AOI T(abs): >80% FROM 325 - 430 nm FOR ALL POLARIZATION @ 45° AOI R(avg):>97% FROM 470 - 545 nm FOR RANDOM POLARIZATION @ 45° AOI R(abs): >95% FROM 470 - 545 nm FOR ALL POLARIZATION @ 45° AOI T(abs): = 50% 450nm @ 45° AOI

(db3). 00% 1001111 0 10

\$1: HARD COATED \$2: SINGLE LAYER MgF2

4. FINE GRIND SURFACE

- POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 6. TRANSMITTED WAVEFRONT DISTORTION RMS@ 632.8nm ≤ ¼ λ
- 7. ROHS COMPLIANT



SHORTPASS FILTER





ϕ 25.00 $_{-0.10}^{0.00}$	1.05±0.10
	\$1-\$2

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

		\$1	S2
ł	SHAPE	PLANO	PLANO
	SURFACE QUALITY	60-40	60-40
	CLEAR APERTURE	Ø22.00	Ø22.00
	BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED

GO	Edmund Optics®
	450 OF DIALIETED DIGUIDOLO

_					
	THIRD ANGLE _ PROJECTION		TITLE	450nm, 25mm DIAMETER, DICHROI SHORTPASS	С
	ALL DIMS IN	mm	DWG NO	69201	SHEET 1 OF 1